

Product: Oxidized Polyethylene Wax

Properties	Value	Unit	Standard
Viscosity @ 140°C	25±10	cP	ASTM D 3236
R&B softening point	105±3	°C	ASTM E28
Melting point	100±10	°C	DSC
Density	0.92±0.01	g/mL	ASTM D 611
Volatile Content @ 150°C	<1	%	ASTM D 6658
Acid number	13±3	mg KOH/G	ASTM D664
Form	Flake	-	-
Color	White	-	-

Application:

- Highly effective External lubricant for PVC
- Polyolefin base masterbatch
- Highly effective External lubricant for PP base masterbatch

Packaging & Storage:

OPE Wax 2402 packed 25 kg BOPP bags. It should be stored in a cold and dry place