

BCX 5842

Product Description

BCX 5842 could be used in injection molding of drippers and extrusion of drip irrigation pipes when some resistance to weathering is requires.

Physical Properties	Nominal Value Unit	Test Method
Carrier	PE	-
Pigment	CB	-
Compatibility	LDPE, LLDPE, HDPE	-
MFR(190°C – 21.6Kg)	18-25 g/10min	ASTM D 1238
Ash Content (600°C)	<0.6	ASTM D5630
Carbon black content	45±1	ASTM D4218-96
Moisture Content	<1500 ppm	-
Forms	Pellets	-

Packaging and Storage

BCX 5842 supplied in pellet form packed in 25 kg three layer PE bags. BCX 5842 should be stored in a dry place. Under these conditions the product could be hold at least 24 months from date of delivery.

Baniam Chemie Exir